

Product	Description	Visible Light Transmitted	Visible Light Reflected	Solar Energy Transmitted	Solar Energy Reflectance	Solar Energy Absorbance	Total Solar Energy Rejected	Median "U" Factor	Design "U" Factor	Shading Coefficient	UV Rejection	Solar Heat Gain Coefficient
Designer Gray												
DG-35	Designer Gray	38%	20%	33%	23%	44%	56%	1	1.04	0.51	99%	0.44
DG-45	Designer Gray	42%	13%	40%	15%	45%	49%	1.06	1.1	0.58	99%	0.50
DG-55	Designer Gray	51%	11%	47%	14%	39%	43%	1.07	1.11	0.66	99%	0.57
Starlite												
SL-280	Starlite	28%	33%	23%	35%	42%	66%	1.02	1.06	0.39	99%	0.34
SL-380	Starlite	37%	21%	32%	22%	46%	53%	1.09	1.13	0.54	99%	0.47
Soft Bronze												
SB-25	Soft Bronze	25%	32%	20%	40%	40%	70%	0.98	1.03	0.34	99%	0.30
SB-35	Soft Bronze	35%	26%	29%	32%	39%	61%	1.01	1.06	0.44	99%	0.38
Safety												
DG-35 4Mil	Designer Gray	38%	20%	33%	23%	44%	56%	1	1.04	0.51	99%	0.44
DG-45 4Mil	Designer Gray	42%	13%	40%	15%	45%	49%	1.06	1.1	0.58	99%	0.50
DG-35 8Mil	Designer Gray	38%	20%	33%	23%	44%	56%	1	1.04	0.51	99%	0.44
DG-45 8Mil	Designer Gray	42%	13%	40%	15%	45%	49%	1.06	1.1	0.58	99%	0.50
Specs on 1/8" glass												